

1.2738

PDF-1

40CrMnNiMo8-6-4

Comprimento: 500 mm

Espessura: +0,4/-0 mm Comprimento: +15/-0 mm Largura: +3/-0mm

Estado de fornecimento: max. 325 HB

Análise química

C: 0,35 – 0,45 Si: 0,2 – 0,4 Mn: 1,3 – 1,6 P: 0 – 0,003 S: 0 – 0,003

Cr: 1,8 – 2,1 Mo: 0,15 – 0,25 Ni: 0,9 – 1,2

Espessura (mm)

Larg.	8,3	10,3	12,3	15,3	20,3	25,3	30,3	40,3	50,3	60,3	70,3	80,3	90,3	100,3	120,3	140,3	150,3
33	x	x	x	x	x	x	X										
43	x	x	x	x	x	x	x	X									
53	x	x	x	x	x	x	x	x	X								
63	x	x	x	x	x	x	x	x	x	X							
73	x	x	x	x	x	x	x	x	x	x	X						
83	x	x	x	x	x	x	x	x	x	x	x	X					
93	x	x	x	x	x	x	x	x	x	x	x	x	X				
103	x	x	x	x	x	x	x	x	x	x	x	x	x	X			
123	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x		
143	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
153	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
163	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
183	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
203	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
223	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
243	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
253	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
263	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
283	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
303	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x