

1.1730 PDF-1 C45U Comprimento: 1000 mm

Aço plano de precisão sem tolerância dimensional para macação

Espessura: + 0,25 / - 0 mm Comprimento: + 35 / - 0 mm Largura: + 0,4 / - 0 mm

Estado de fornecimento: max. 190 HB

Análise química

C: 0,42 – 0,5 Si: 0,15 – 0,4 Mn: 0,6 – 0,8 P: 0 – 0,03 S: 0 – 0,03

Espessura (mm)

Larg.	4,0	5,0	6,0	8,0	10,0	12,0	15,0	16,0	20,0	25,0	30,0	32,0	40,0	50,0	60,0	63,0	70,0	80,0	100,0	120,0	150,0
10,0				X																	
12,0						x															
15,0							x														
16,0								x													
20,0	x	x	x	x	x	x	x	x	x	x											
25,0	x	x	x	x	x	x	x	x	x	x	x	x									
30,0	x	x	x	x	x	x	x	x	x	x	x	x									
32,0	x	x	x	x	x	x	x	x	x	x	x	x									
40,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x				
50,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x				
60,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
63,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x				
70,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
80,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
90,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
100,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
120,0		x	x	x	x	x	x		x	x	x		x	x	x	x	x	x	x	x	
125,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
140,0	x	x	x	x	x	x	x	x	x	x		x	x	x	x	x	x	x	x	x	
150,0	x	x	x	x	x	x	x	x	x	x		x	x	x	x	x	x	x	x	x	x
160,0	x	x	x	x	x	x	x	x	x	x		x	x	x	x	x	x	x	x	x	x
175,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
180,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
200,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
225,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
250,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
300,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
315,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
350,0		x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
400,0	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
450,0									x	x	x	x	x	x	x	x	x	x	x	x	x
500,0									x	x	x	x	x	x	x	x	x	x	x	x	x