

1.2842/1.2510 PDF-1 90MnCrV8/100MnCrW4 Comprimento: 500 mm

**Aço plano de precisão sem tolerância dimensional para maquinagem**

Espessura: +0,05 /-0 mm Comprimento: +15/-0 mm Largura: +0,2 /-0mm

Estado de fornecimento: max. 229 HB

**Análise química**C: 0,85 – 0,95 Si: 0,1 – 0,4 Mn: 1,8 – 2,2 P: 0 – 0,03 Cr: 0,2 – 0,5  
V: 0,05 – 0,2**Espessura (mm)**

Larg.	1,0	1,5	2,0	3,0	4,0	5,0	6,0	8,0	10,0	12,0	15,0	16,0	18,0	20,0	25,0	30,0	40,0	50,0	60,0
4,0				x															
5,0					x														
6,0						x													
8,0							x												
10,0	x	x	x	x	x	x	x	x	x										
12,0	x	x	x	x	x	x	x	x	x	x	x								
15,0	x	x	x	x	x	x	x	x	x	x	x	x							
16,0												x							
18,0													x						
20,0	x	x	x	x	x	x	x	x	x	x	x			x					
25,0	x	x	x	x	x	x	x	x	x	x	x			x	x				
30,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x			
35,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x			
40,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x		
50,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	
60,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
70,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
80,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
100,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
120,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
125,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
150,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
160,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
180,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
200,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
250,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x
300,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x