

1.2990 PDF-1 ~X100CrMoV8-1-1

Comprimento: 500 mm

Espessura: +0,4/-0 mm Comprimento: +15/-0 mm Largura: +3/-0mm

Estado de fornecimento: max. 250 HB

Análise química

C: 1,0 - 1,0 Si: 0,9 - 0,9 Cr: 8,0 - 8,0 Mo: 1,6 - 1,6 V: 1,6 - 1,6

Espessura (mm)

Larg.	15,3	20,3	25,3	30,3	35,3	40,3	50,3	60,3	70,3	80,3				
33	X	X	X	X										
43	x	x	x	x	x	X								
53	x	x	x	x	x	x	X							
63	x	x	x	x	x	x	x	X						
73	x	x	x	x	x	x	x	x	x	x				
83	x	x	x	x	x	x	x	x	x	x	X			
93	x	x	x	x	x	x	x	x	x	x	X			
103	x	x	x	x	x	x	x	x	x	x	X			
123	x	x	x	x	x	x	x	x	x	x	X			
143	x	x	x	x	x	x	x	x	x	x	X			
153	x	x	x	x	x	x	x	x	x	x	X			
163	x	x	x	x	x	x	x	x	x	x	X			
183	x	x	x	x	x	x	x	x	x	x	X			
203	x	x	x	x	x	x	x	x	x	x	X			
223	x	x	x	x	x	x	x	x	x	x	X			
243	x	x	x	x	x	x	x	x	x	x	X			
253	x	x	x	x	x	x	x	x	x	x	X			
263	x	x	x	x	x	x	x	x	x	x	X			
283	x	x	x	x	x	x	x	x	x	x	X			
303	x	x	x	x	x	x	x	x	x	x	X			
323	x	x	x	x	x	x	x	x	x	x	X			
343	x	x	x	x	x	x	x	x	x	x	X			
353	x	x	x	x	x	x	x	x	x	x	X			
363	x	x	x	x	x	x	x	x	x	x	X			
383	x	x	x	x	x	x	x	x	x	x	X			
403	x	x	x	x	x	x	x	x	x	x	X			
423	x	x	x	x	x	x	x	x	x	x	X			
443	x	x	x	x	x	x	x	x	x	x	X			
453	x	x	x	x	x	x	x	x	x	x	X			
463	x	x	x	x	x	x	x	x	x	x	X			
483	x	x	x	x	x	x	x	x	x	x	X			
503	x	x	x	x	x	x	x	x	x	x	X			